



R SILVER 15 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	15
% VISIBLE LIGHT REFLECTANCE	68
% SOLAR TRANSMITTANCE	12
% SOLAR REFLECTANCE	56
% SOLAR ABSORBANCE	32
SHADING COEFFICIENT	0.24
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	79
% GLARE REDUCTION	84

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R SILVER 35 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	41
% VISIBLE LIGHT REFLECTANCE	29
% SOLAR TRANSMITTANCE	31
% SOLAR REFLECTANCE	27
% SOLAR ABSORBANCE	41
SHADING COEFFICIENT	0.49
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	58
% GLARE REDUCTION	55

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R SILVER 50 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	55
% VISIBLE LIGHT REFLECTANCE	24
% SOLAR TRANSMITTANCE	43
% SOLAR REFLECTANCE	24
% SOLAR ABSORBANCE	33
SHADING COEFFICIENT	0.60
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	48
% GLARE REDUCTION	39

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R GREY 10 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	8
% VISIBLE LIGHT REFLECTANCE	18
% SOLAR TRANSMITTANCE	9
% SOLAR REFLECTANCE	57
% SOLAR ABSORBANCE	34
SHADING COEFFICIENT	0.26
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	76
% GLARE REDUCTION	91

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R BRONZE 10 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	10
% VISIBLE LIGHT REFLECTANCE	25
% SOLAR TRANSMITTANCE	8
% SOLAR REFLECTANCE	39
% SOLAR ABSORBANCE	53
SHADING COEFFICIENT	0.24
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	79
% GLARE REDUCTION	89

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NR BRONZE 35 NON-REFLECTIVE

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	32
% VISIBLE LIGHT REFLECTANCE	7
% SOLAR TRANSMITTANCE	56
% SOLAR REFLECTANCE	7
% SOLAR ABSORBANCE	37
SHADING COEFFICIENT	0.77
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	33
% GLARE REDUCTION	64

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



BLACK OUT

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	0
% VISIBLE LIGHT REFLECTANCE	5
% SOLAR TRANSMITTANCE	0
% SOLAR REFLECTANCE	34
% SOLAR ABSORBANCE	66
SHADING COEFFICIENT	0.21
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	82
% GLARE REDUCTION	100

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



WHITE OUT

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	8
% VISIBLE LIGHT REFLECTANCE	59
% SOLAR TRANSMITTANCE	11
% SOLAR REFLECTANCE	47
% SOLAR ABSORBANCE	41
SHADING COEFFICIENT	0.27
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	77
% GLARE REDUCTION	91

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SAFETY 2 MIL CLEAR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	87
% VISIBLE LIGHT REFLECTANCE	9
% SOLAR TRANSMITTANCE	83
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	9
SHADING COEFFICIENT	0.9
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	2
% GLARE REDUCTION	1

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SAFETY 4 MIL CLEAR

THICKNESS OF FILM (MIL)	4
% VISIBLE LIGHT TRANSMITTANCE	87
% VISIBLE LIGHT REFLECTANCE	9
% SOLAR TRANSMITTANCE	79
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	13
SHADING COEFFICIENT	0.96
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	2
% GLARE REDUCTION	1

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SAFETY 7 MIL CLEAR

THICKNESS OF FILM (MIL)	7
% VISIBLE LIGHT TRANSMITTANCE	87
% VISIBLE LIGHT REFLECTANCE	10
% SOLAR TRANSMITTANCE	79
% SOLAR REFLECTANCE	8
% SOLAR ABSORBANCE	13
SHADING COEFFICIENT	0.95
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	2
% GLARE REDUCTION	0

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SAFETY 12 MIL CLEAR

THICKNESS OF FILM (MIL)	12
% VISIBLE LIGHT TRANSMITTANCE	87
% VISIBLE LIGHT REFLECTANCE	10
% SOLAR TRANSMITTANCE	78
% SOLAR REFLECTANCE	9
% SOLAR ABSORBANCE	13
SHADING COEFFICIENT	0.95
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	4
% GLARE REDUCTION	2

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



UV 2MIL CLEAR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	89
% VISIBLE LIGHT REFLECTANCE	6
% SOLAR TRANSMITTANCE	81
% SOLAR REFLECTANCE	6
% SOLAR ABSORBANCE	13
SHADING COEFFICIENT	0.98
% ULTRA VIOLET TRANSMITTANCE	<1
% TSER	15
% GLARE REDUCTION	2

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R BLUE 15 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	13
% VISIBLE LIGHT REFLECTANCE	31
% SOLAR TRANSMITTANCE	11
% SOLAR REFLECTANCE	37
% SOLAR ABSORBANCE	52
SHADING COEFFICIENT	0.29
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	75
% GLARE REDUCTION	86

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R GOLD 15 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	14
% VISIBLE LIGHT REFLECTANCE	52
% SOLAR TRANSMITTANCE	13
% SOLAR REFLECTANCE	53
% SOLAR ABSORBANCE	34
SHADING COEFFICIENT	0.25
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	78
% GLARE REDUCTION	84

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R GREY 10 EXTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	8
% VISIBLE LIGHT REFLECTANCE	18
% SOLAR TRANSMITTANCE	9
% SOLAR REFLECTANCE	57
% SOLAR ABSORBANCE	34
SHADING COEFFICIENT	0.26
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	76
% GLARE REDUCTION	91

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R GREEN 10 INTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	10
% VISIBLE LIGHT REFLECTANCE	24
% SOLAR TRANSMITTANCE	10
% SOLAR REFLECTANCE	37
% SOLAR ABSORBANCE	53
SHADING COEFFICIENT	0.27
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	76
% GLARE REDUCTION	89

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



R SILVER 20 EXTERIOR

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	17
% VISIBLE LIGHT REFLECTANCE	55
% SOLAR TRANSMITTANCE	12
% SOLAR REFLECTANCE	49
% SOLAR ABSORBANCE	38
SHADING COEFFICIENT	0.26
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	78
% GLARE REDUCTION	81

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NF SOLAR BRONZE 20

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	18
% VISIBLE LIGHT REFLECTANCE	46
% SOLAR TRANSMITTANCE	11
% SOLAR REFLECTANCE	62
% SOLAR ABSORBANCE	27
SHADING COEFFICIENT	0.24
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	79
% GLARE REDUCTION	80

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



NF SOLAR BRONZE 35

THICKNESS OF FILM (MIL)	2
% VISIBLE LIGHT TRANSMITTANCE	33
% VISIBLE LIGHT REFLECTANCE	32
% SOLAR TRANSMITTANCE	21
% SOLAR REFLECTANCE	50
% SOLAR ABSORBANCE	29
SHADING COEFFICIENT	0.31
% ULTRA VIOLET TRANSMITTANCE	<2
% TSER	73
% GLARE REDUCTION	63

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.